



REVISIONS			DOC. NO. SPC-F004 * Effective: 7/8/02 * DCP No: 1398						
DCP #	REV	DESCRIPTION	DRAWN	DATE	CHECKD	DATE	APPRVD	DATE	
1534	D	Removed LTP-004-4025-BLK	JWM	5/14/03	JC	5/20/03	JC	5/20/03	
1857	E	RoHS Added	DCM	12/12/05	JWM	3/17/06	JWM	3/17/06	

The **LTP** series is the most flexible of the heat-shrinkable, polyolefin tubings. The LTP series has been engineered to offer a low shrink temperature. This allows the tubing to shrink rapidly, thereby minimizing heat exposure and possible damage to sensitive substrate materials or components.



Shrink Ratio: 2:1 Shrink Temperature: 100°C (212°F) Color: Black

Dimensions				Standard Packages					
			Recovered	4 Foot Lengths (+1", -0")			6 Inch Lengths (±.125")		
Size	Expanded I.D.	Recovered I.D.	Nominal Wall Thickness	SPC Type No.	Qty	Total Footage	SPC Type No.	Qty	Total Footage
3/64"	.046"	.023"	.016"	LTP-003-4025-BLK	25	100 FT	LTP-003-6040-BLK	40	20 FT
1/16"	.063"	.031"	.017"	N/A			LTP-004-6036-BLK	36	18 FT
3/32"	.093"	.046"	.020"	LTP-006-4025-BLK	25	100 FT	LTP-006-6018-BLK	32	16 FT
1/8"	.125"	.062"	.020"	LTP-008-4025-BLK	25	100 FT	LTP-008-6028-BLK	28	14 FT
3/16"	.187"	.093"	.020"	LTP-012-4025-BLK	25	100 FT	LTP-012-6025-BLK	24	12 FT
1/4"	.250"	.125"	.025"	LTP-016-4025-BLK	25	100 FT	LTP-016-6020-BLK	20	10 FT
3/8"	.375"	.187"	.025"	LTP-024-4025-BLK	25	100 FT	LTP-024-6020-BLK	16	8 FT
1/2"	.500"	.250"	.025"	LTP-032-4005-BLK	5	20 FT	LTP-032-6016-BLK	14	7 FT
3/4"	.750"	.375"	.030"	LTP-048-4005-BLK	5	20 FT	LTP-048-6012-BLK	12	6 FT
1"	1.000"	.500"	.035"	LTP-064-4005-BLK	5	20 FT	LTP-064-6008-BLK	8	4 FT
1 1/2"	1.500"	.750"	.040"	LTP-096-4005-BLK	5	20 FT	N/A	---	---
2"	2.000"	1.000"	.045"	LTP-128-4005-BLK	5	20 FT	N/A	---	---

TYPICAL PROPERTIES

Physical

Tensile Strength 2100 PSI
Ultimate Elongation 450%
Longitudinal Change ±5%
Secant Modulus (2%) 11,000 PSI
Heat Aging Elongation (168 hrs @ 175°C) 200%(Min)250%
Heat Shock (4 hrs @ 250°C) No dripping, cracking, passes mandrel wrap test
Low Temperature Flexibility (4 hrs @ -55°C) No Cracking
Flammability Self extinguishing meets UL 224 all tubing flame test

Flexibility*: 2

Electrical

Dielectric Strength 800 V/mil
Volume Resistivity 10^{14} ohm-cm

Chemical

Corrosive Effect Non-corrosive
Solvent Resistance
Tensile Strength 750 PSI
Dielectric Strength 400 V/mil
Water Absorption 0.2%
Fungus Resistance Non-nutrient
Applicable Specifications: MIL-R-46846 Type V, AMS-3587



The technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

*Flexibility: The materials are rated on a scale of 1~10.
1=most flexible and 10=most rigid

SPC-F004.DWG

TOLERANCES: UNLESS OTHERWISE SPECIFIED, DIMENSIONS ARE FOR REFERENCE PURPOSES ONLY.	DRAWN BY:	DATE:	DRAWING TITLE:			
	JAP	1/22/92	LTP Series - Polyolefin Heat Shrink Tubing			
	CHECKED BY:	DATE:	SIZE	DWG. NO.	ELECTRONIC FILE	REV
	JC	1/29/92	A	TA-403	TA-403.dwg	E
	APPROVED BY:	DATE:	SCALE: NTS		U.O.M.: INCHES [mm]	SHEET: 1 OF 1
	JC	1/29/92				

ALL RIGHTS RESERVED. NO PORTION OF THIS PUBLICATION, WHETHER IN WHOLE OR IN PART CAN BE REPRODUCED WITHOUT THE EXPRESS WRITTEN CONSENT OF SPC TECHNOLOGY. DISCLAIMER: ALL STATEMENTS AND TECHNICAL INFORMATION CONTAINED HEREIN ARE BASED UPON INFORMATION AND/OR TESTS WE BELIEVE TO BE ACCURATE AND RELIABLE. SINCE CONDITIONS OF USE ARE BEYOND OUR CONTROL, THE USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE AND ASSUME ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.