

KAMCY® 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/0 0	页 码 Pagination	1/11

客 户
Customer

产品规格书

Specification for products

电池类型：圆柱型锂离子电池

Cell model:Cylindrical Li-ion Battery

电池型号： IFR18650-20FE

Cell type:IFR18650-20FE

编 制 Compilation		Date	深圳市康胜新能源产品有限公司 生效2024. 05. 08日期 工程承认章
审 核 Checked		日期 Date	
批 准 Approved		日期 Date	

客户签字确认/日期 Customer Approval/Date	
-------------------------------------	--



文件序号
Document number

产品规格书

Specification for products

$$\begin{array}{c} A/0 \\ 0 \end{array}$$


页 码
~~Pagination~~

2/11

修订履历Version change record

[illegible]


KAMCY® 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/00	页 码 Pagination	3/11



目录Contents

- 1 前言Preface
- 2定义Definition
 - 2.1 标准充电方式Standard charge method
 - 2.2 标准放电方式Standard discharge method
 - 2.3 标称容量Rated capacity
- 3 电芯型号、尺寸Cell type &cell dimension
 - 3.1 电芯型号Cell type
 - 3.2 电芯尺寸Cell dimensions
- 4 电芯特性Cell characteristics
- 5 技术要求Technicalrequirements
 - 5.1 电芯使用环境Cell usage conditions
 - 5.2电芯试验环境Cellexperimental environmet
 - 5.3电性能Electronic performance
 - 5.4安全性能Safty performance
- 6包装图片Package picture
- 7 出货Shipment
- 8 质量保证Warranty
- 9存储及运输要求Storage and shipment requirement
- 10 电芯使用时警告事项及注意事项Warning &attention in usage of lithium-ion cel
- 11有害物质控制要求Control requirements for hazardous substances

KAMCY® 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/0 0	页 码 Pagination	4/11



1 前言Preface

1.1. 本规格书描述了我司圆柱型锂离子电芯的外型尺寸、特性、技术要求及注意事项。本标准适用于深圳市康胜新能源产品有限公司生产的圆柱型IFR18650-20FE锂离子电芯。

This specification describes the type and dimensions, performance, technical characteristics, warning and attention of the lithium LI-ion cell for our company. The specification only applies to IFR18650-20FE cell supplied by Shenzhen Kamcy New Energy Products Co., Ltd.

2 定义Definition

2.1 标准充电方式: Standard charge method

指在25.0±2℃环境下,以0.5CsA的电流恒流充电至单体电芯电压3.65后,转为恒压3.65 充电,至充电电流小于0.01CA时,停止充电。Under 25±2℃, it can be charged to 3.65V with constant current of 0.5CA, and then, charged continuously with constant voltage of 3.65V until the charged current is 0.01CA.

2.2标准放电方式: Standard discharge method

指在25.0±2℃环境下,以0.5CA的电流恒流放电至单体电芯电压2.0 V。Under 25±2℃, it can be discharged to the voltage of 2.0V with constant current of 0.5CA.

2.3 标称容量: Rated capacity

指在25.0±2℃环境下,以0.2CA的电流恒流充电至单体电芯电压3.65±0.05V后转为恒压3.65±0.05 V充电,0.2CsA放电至终止电压2.0V时的容量,以Cap表示,单位为毫安时(mAh)。Rated capacity refers to under 25±2℃, charge at 0.2CA to end voltage 3.65±0.05V, then discharge at 0.2CA to the end voltage 2.0V, which is signed Cap, the unit is mAh


3 电芯型号、尺寸Cell type and dimensions

3.1 电芯型号 Cell type

电芯说明Description:圆柱锂离子二次电芯Cylindrical Li-ion rechargeable cell型号Model IFR18650-20FE

3.2电芯尺寸cell dimensions

电芯尺寸示意图如图所示(单位: mm)。Cell physical dimensions listed in Figure 3(unit:mm)



KAMCY® 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/00	页 码 Pagination	5/11

深圳市康胜新能源产品有限公司


生效2024.05.08日期

工程承认章

4 电芯特性 Cell specification

项目ITEM	特征specification
标称容量 Normal capacity	2000mAh discharge to 2.0V with 0.2CA
最小容量 Min Capacity	≥1950mAh (The cell will be charged at 0.5CA to Voltage 3.65 ±0.05V ,and then discharge to 2.0V with 0.5C A)
标称电压 Normal voltage	3.2V
最大充电电压 Max charging voltage	3.65V
放电终止电压 Discharge ending voltage	2.0V
标准充电电流 Standard charging current	0.5C ₅ A
最大充电电流 Max charging current	1C ₅ A
最大放电电流 Max discharging current	3C ₅ A
内阻(不带PTC) Internal resistance(with out PTC)	IR≤40 mΩ
电芯尺寸(含膜) Cell dimensions(diaphrag)	最大高度Max Height:65.3 mm 最大直径Max diameter:18.4 mm
单颗电池重量 single cell Weight	≤45g

KAMCY[®] 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/00	页 码 Pageation	4/11



5 技术要求Technical requirements

5.1 电芯使用环境 Cell usage conditions

Charge temperature 充电温度： 0~55 ℃

Discharge temperature 放电温度： -20~60 ℃

5.2 电芯试验环境 Cellexperimental environmet

Unless otherwise specified,all tests stated should be done at 25±2℃.

除非有特殊说明，所有测试须在25±2℃下完成。

5.3 电性能 Electronic performance


序 号 NO.	测试项目 Item	性能标准 Performance standardS	测试条件与方法 Test conditions and methods
5.3.1	倍率放电 Rate discharge	放电容量/标称容量 Discharge capacity /Nominal capacity *100%×100% A) 0.2CA ≥102% B) 0.5CA ≥100% C) 1CA ≥98% D) 3C ₅ A ≥95%	电池标准充电至满电后，搁置15min, 分别以0.2CA、0.5CA、1CA、3C ₅ A进行放电至下限电压2.0V, 循环三次，当有一次达到标准，即达到标准要求After standard charge, rest for 15min and then discharge at 0.2CA, 0.5CA, 1CA and 3CA to discharge cut-offvoltage2.0V respectively. Charge/discharge cycle can be conducted for 3 times before meeting the Standards.
5.3.2	循环寿命 Cycle Life	容量(800周) ≥80% Capacity(1000th) cycle ≥80%	测量电池的初始状态和初始容量，进行0.5CA/1CA循环，800次后测量电池的最终状态。Measure the initial condition and initial capacity of the cell. Then conduct 0.5C ₅ A/1C ₅ A, 1000th cycle to measure the final condition of the cell.

KAMCY® 深圳市康胜新能源产品有限公司		文件名称 Document name	产品规格书 Specification for products		
		文件序号 Document number			
		版 本 Version	A/00	页 码 Pagination	7/11
5.3.3	高温性能 Hightemperatue discharging performance	容量Capacity55℃≥100% 容量Capicity60℃≥95%	深圳市康胜新能源产品有限公司 生2024.05.08日 工程承认章 测量电池的初始容量和初始状态，电池标准充电后，在55±2℃/60±2℃条件下恒温搁置2h、以0.2CA放电至2.0V Measure the initial condition and initial capacity of the cell,keep the cell for 2h in 55±2℃/60±2℃ ,then discharge at 0.2CA to 2.0V		
5.3.4	低温性能 LowTemperature Performance	容量-10℃≥60% Capicity-10℃≥60% 容量0℃≥70% Capicity0℃≥70%	测量电池的初始容量和初始状态，电池标准充电后，在-10±2℃/0±2℃的恒温条件下搁置4h,以0.2CA放电至2.0V Measure the cell initial capacity and inital state,after the stangard charge,keep the cell for 4h in -10℃/0±2℃,then discharge at 0.2CA to 2.0V		
5.3.5	常温荷电保持能大 Normal Storage	剩余容量≥标称容量*90% 恢复容量≥标称容量*95% Residual capacity ≥Nominal capacity *90% Recovery capacity ≥Nominal capacity *95%	测量电池的初始状态和初始容量，电池标准充电后，开路放置30天，测量电池最终状态；以0.5CA放电至2.0V,测量电池的剩余容量；0.5CA/0.5CA测量电池的恢复容量。可循环三次，当有一次达到标准，即达到标准要求。 Tested the initial condition and initial capacity of battery.Store for 28 days after standard charged, tested the final condition of battery.Then discharge at 0.5CA to the discharge cut-off voltage 2.0V tested the residualcapacity of battery.0.5CA /0.5CA tested the recovery capacity of battery. Charge/discharge cycle can be conducted for 3 times before meeting the Standards.		

5.4 安全性能Safty performan


KAMCY® 深圳市康胜新能源产品有限公司		文件名称		产品规格书	
		Document name		Specification for products	
		文件序号			
		Document number			
		版 本		页 码	
		Version		Pagination	
		A/00		8/11	
深圳市康胜新能源产品有限公司 生 2024.05.08 日期 工程承认章					
序号	测试项目	性能标准	测试条件与方法		
NO	Item	Performance standards	Test conditions and methods		
5.4.1	振动性能 Vibration	不漏液、不起火、不爆炸，电芯电压不低于3.2V No leakage, No fire No explosion, voltage is no less than 3.2V	电池标准充电充满后，测量电池初始状态，安装在振动台面上，按下面的振动频率和对应的振幅调整好试验设备，X、Y、Z三个方向每个方向上从7Hz~200Hz 循环扫频振动3h. After standard charge. Measure the cell initial state. Equip it to the vibration platform, adjust and prepare the test equipment according to following vibration frequency and relevant swing, doing frequency sweeping from X, Y, Z three directions, each from 7Hz to 200Hz for 3 hours of recycling		
5.4.2	过充性能 Overcharge test	不起火、不爆炸 No fire, No explosion	电芯按照标准放电至终止电压，然后将电芯置于通风橱中，连接电芯正负极与电源，调节电流至3CA，电芯充电电压为4.6V。监视电芯温度变化，当电芯温度下降到比峰值低约10℃，结束试验。Standard discharge to the ending voltage. Then place the cell in the fume cupoard, connect the positive and negative power supply, ad just current to 3CA, change to 4.6V. Observe the variation of the cell' s temperature. Finish the test when the cell drops to 10℃		
5.4.3	强制放电 Forced discharge	电芯不起火、不爆炸 No fire, No explosion	电芯以0.2C ₅ A的电流恒流放电至单体电芯电压2.0V，然后以1ItA的电流对电芯进行反向充电，要求充电时间不低于90min。Discharge at 0.2CA to 2.0V, and then reverse charge the cell at 1 ITA for 90min		
5.4.4	130℃热冲击 Hot oven	电芯不起火、不爆炸 No fire, No explosion	电芯按照标准充电方式充满电后，将电芯放进热箱里，然后将热箱按5℃/min升温到130℃，电芯在热箱130℃环境下保持30分钟，记录电芯温度升至130℃起的时间。Standard charge. Keep the cell connected with a thermocouple and put it into a gravity convection or circulating air oven Temperature is raised at a rate of 5℃per minute to a temperature of 130 Cand remained for 30min at this temperature. Observe the variation of the cell' s appearance		

KAMCY® 深圳市康胜新能源产品有限公司	文件名称	产品规格书		
	Document name	Specification for products		
	文件序号			
	Document number			
	版本	A/00	页 码	4/11
	Version		Pagination	



5.5.5	短路测试 Shortcircuit test	不起火、不爆炸、温度 <150℃ No fire, No explosion <150℃	电芯按照标准充电方式充满电后, 2024年接有热电偶的电芯置于通风橱中, 用铜线短路其正负极(线路总电阻不大于50毫欧), 实验过程中监视电芯温度变化, 当电芯温度下降到比峰值低10℃时, 结束实验。 Standard charge. Keep the battery into a ventilation cabinet and short-circuit the positive and negative terminals directly. Stop the test when the temperature falls to 10 °C lower than the peak value. Observe the variation of the battery's appearance and temperature.
5.5.6	重物冲击测试 Impact test	不起火、不爆炸 No fire, No explosion	电芯按照标准充电方式充满电后, 水平放置于一个与电芯纵轴平行的平板。将一直径Φ7.9mm的棒放在样品中心, 让重量9.1±0.1kg的重物从610±25mm的高度落到实验电芯上方的钢柱上, 测试完毕观察6h。 Standard charge. Placed the battery in a plane, and connected with the thermocouple. Take a diameter of 7.9 mm steel column (9.1kg) in the 610 mm height and middle of battery. Let it freedom to impact the battery. Observe the variation of the battery's appearance and temperature for 6 h.
5.5.7	挤压测试 Crush test	不起火、不爆炸 No fire, No explosion	电芯按照标准充电方式充满电后, 放在两个平整的表面进行挤压测试, 压力器必须施加一个与圆柱电芯轴向垂直的力, 平压于电芯。所用压力为13 KN, 一旦达到最大压力值, 即释放压力。 After charging a cell following the standard charge method, the cell shall be crushed between two flat surfaces. The direction of the crushing force shall be vertical to axis of the cylinder. The crushing force is to be Crushing force is approximately 13 KN. Once the maximum pressure has been obtained it is to be released

KAMCY® 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/00	页 码 Pagination	4/11



6 包装图片Package picture



100pcs battery in a small box,4 small boxes in a big box)

Note:According to customer requirements,the color of PVC film will be different.

7 出货 Shipment

单体电芯按≥3.3V 的充电电压或客户要求出货，电芯出货后充电前的剩余容量取决于储存时间和条件。

The Cell shall be shipped in voltage range of **Greater than or equal to 3.3V** or in accordance with customers'requirement.

The remaining capacity before charging shall be changed depending on the storage time and conditions.

8 质量保证 Warranty

8.1. 客户在收到我司产品时应该在7个工作日内完成进料检验，部分检验周期久的项目可适当延期至一个月，批次验收被判定不合格品经我司确认后给予换货处理；超过7个工作日没有进行来料确认的电芯在没有产品可靠度隐患时我司将不接受批量退换货。

The customer shall complete the incoming material inspection within 7 working days upon receipt of our products,and part of the projects with a long inspection cycle can be properly delayed to 1month. The batch acceptance is determined to be non-conforming products upon our confirmation,and the replacement shall be conducted;Our company will not accept bulk return and exchange of batterys that have not been confirmed with incoming materials for more than 7 working days.


8.2. 我司产品的质量保质期为：自我司产品出货之日起 12 个月。

The quality guarantee period of our products is 12 months from the date of shipment.

9 存储及运输要求 Storage and shipment requirement

项 目 Item	环境 Conditions	允许时间 Permissible time
储存环境 Storage environment	45 ℃~60 ℃, 60%RH Max	少于1个月 Less than 1 month
	25 ℃~45 ℃, 60%RH Max	少于3个月 Less than 3 month
	-20 ℃~25℃, 60%RH Max	少于 1 年 Less than 1 year

KAMCY® 深圳市康胜新能源产品有限公司	文件名称 Document name	产品规格书 Specification for products		
	文件序号 Document number			
	版 本 Version	A/00	页 码 Pagination	4/11



In case of long period storage (more than 3 days), storage the cell at temperature range of -10~+20℃, low humidity, no corrosive gas atmosphere.

如果要长时间存放(超过3天), 电芯存储的较佳温度范围为-10~ +20℃, 低湿度和不含腐蚀性气体的环境中。

- 10电芯使用时警告事项及注意事项Warning and attention in usage of the lithium-ion cell
- 10.1电芯使用警告Warning in usage
- 10.1.1严禁随意拆解电芯。Don't pull the cell optionally
 - 10.1.2严禁将电芯放在热高温源旁, 如火, 加热器等旁边使用和放置。Don't use and leave the cell near a heat source such as fire or heater.
 - 10.1.3严禁将电芯直接插入电源插座。Don't connect the cell to an electrical outlet directly
 - 10.1.4严禁将电芯与金属一起运输或存储。Don't transport and store the cell together with metal objects
 - 10.1.5严禁敲击, 抛掷或踩踏电芯。Don't strike, throw or trample the cell
 - 10.1.6严禁直接焊接电芯。Don't solder the cell directly
 - 10.1.7严禁用利器刺穿电芯。Don't pierce the cell with sharp object
- 10.2电芯使用注意事项Attention in usage
- 10.2.1使用时注意正、负极不能接触, 防止电芯短路。Don't connect the positive and negative directly for avoiding short
 - 10.2.2电芯存储应放置在阴凉干燥的环境中; 长期储存环境温/湿度25.0±2.℃/60±22.5%RH。Cell storage should be kept in a cool, dry environment for long time in 25.0±2.℃/60±22.5%RH
 - 10.2.3电芯在使用前要求表面套绝缘膜, 防止电芯短路。The cell is insulated before usage for avoiding short.
- 11有害物质控制要求The control requirements for hazardous substances
- 本型号锂离子电芯符合本公司“环境物质控制标准”要求!This model of lithium-ion cell is in accordance with our company's request of "environmental substances control standard"!